

TECHNICAL DATASHEET



Brazing alloy BrazeTec 3075

TD EN 3075 REV. 3

Composition (% in weight)

Ag	Cu	Zn	Sn	Si	Р	Mn	Ni	Other	ISO 17672:20 10	EN 1044:1999	ISO 3677
30	38	32	-	-	-	-	-	-	-	AG 204	-

Technical data:

Melting range (°C)	680 - 765			
Working temperature (°C)	750			
Melting range according to DSC measurement (°C)	-			
Min. brazing temperature (°C)	-			
Electrical conductibility (m/ Ω mm ²)	-			
Elongation %	25			
Density (g/cm³)	8,9			
Shear strength (MPa)	-			
Tensile strength DIN EN 12797 (MPa)	with S 235:380; with E 295:430			
Operating temperature of brazed joint (min/max) \pm (°C)	200			

Applications

Refrigeration, air conditioning and electrical industry, plumbing technology

Operating conditions

Silver based brazing alloy with excellent flow, capillarity and mechanical strength characteristics. Used for brazing any steels, copper and copper alloys, as well as nickel and nickel alloys.

Recommended fluxes

N1/T, Super 1, N2/E, H paste, H sprayable, RS/A, FN/E, D 98, H 280

Heat sources

Flame, induction heating, furnace in vacuum and under protective atmosphere

Delivery forms

Wire, rods, ribbon, rings, preforms, powder

Notes

_

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations.

Italbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility.

Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of suitability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.

Tel. +39 0444.3475-00 / Fax +39 0444.3475-01