

# **TECHNICAL DATASHEET**



## **Brazing alloy BrazeTec 3876**

**TD EN 3876 REV. 5** 

### **Composition (% in weight)**

Ag	Cu	Zn	Sn	Si	Р	Mn	Ni	Other	ISO 17672:20 10	EN 1044:1999	ISO 3677
38	31	29	2	-	-	-	-	-	Ag 138	-	-

#### **Technical data:**

Melting range (°C)	650-720		
Working temperature (°C)	720		
Melting range according to DSC measurement (°C)	-		
Min. brazing temperature (°C)	-		
Electrical conductibility (m/ $\Omega$ mm <sup>2</sup> )	-		
Elongation %	-		
Density (g/cm³)	9,1		
Shear strength (MPa)	-		
Tensile strength DIN EN 12797 (MPa)	-		
Operating temperature of brazed joint (min/max) $\pm$ (°C)	-		

## **Applications**

Refrigeration, air conditioning and electrical industry, plumbing technology

## **Operating conditions**

Silver based brazing alloy with excellent flow, capillarity and mechanical strength characteristics. Used for brazing any steels, copper and copper alloys, as well as nickel and nickel alloys.

#### Recommended fluxes

N1/T, Super 1, N2/E, H paste, H sprayable, RS/A, FN/E, D 98, H 280

#### **Heat sources**

Induction heating, flame, furnace in vacuum and under protective atmosphere

#### **Delivery forms**

Wire, rods, ribbon, rings, preforms, powder

## Notes

\_

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations.

Italbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility.

Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of suitability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.