

TECHNICAL DATASHEET



Brazing alloy BrazeTec 2500

TD EN 2500 REV. 4

Composition (% in weight)

Ag	Cu	Zn	Sn	Si	P	Mn	Ni	Other	ISO 17672:2010	EN 1044:1999	ISO 3677
25	40	35	-	-	0	-	-	-	AG 225	AG 205	-

Technical data:

Melting range (°C)	700-790			
Working temperature (°C)	780			
Melting range according to DSC measurement (°C)	-			
Min. brazing temperature (°C)	-			
Electrical conductibility (m/ Ω mm ²)	-			
Elongation %	25			
Density (g/cm³)	8,9			
Shear strength DIN EN 12797 (MPa)	-			
Tensile strength DIN EN 12797 (MPa)	with S 235:380; with E 295:430			
Operating temperature of brazed joint (min/max) \pm (°C)	200			

Applications

Refrigeration, air conditioning and electrical industry, plumbing technology

Operating conditions

Silver based brazing alloy with excellent flow, capillarity and mechanical strength characteristics. Used for brazing any steels, copper and copper alloys, as well as nickel and nickel alloys.

Recommended fluxes

N1/T, Super 1, N2/E, H paste, H sprayable, RS/A, FN/E, D 98, H 280

Heat sources

Flame, induction heating, furnace in vacuum and under protective atmosphere

Delivery forms

Wire, rods, ribbon, rings, preforms, powder

Notes

14010

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations.

trialbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility.

the use or application intended by him on his own responsibility.

Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of suitability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.