



Brazing alloy BrazeTec 3876

Composition (% in weight)

Ag	Cu	Zn	Sn	Si	Р	Mn	Ni	Other	ISO 17672	EN 1044	ISO 3677
38	32	28	2	-	-	-	-	-	Ag 138	-	-

Technical data:

Melting range (°C)	650-720
Working temperature (°C)	720
Melting range according to DSC measurement (°C)	-
Min. brazing temperature (°C)	-
Electrical conductibility (m/Ω mm²)	-
Elongation %	-
Density (g/cm3)	9,1
Shear strength (MPa)	-
Tensile strength DIN EN 12797 (MPa)	-
Operating temperature of brazed joint (min/max) ± (°C)	

Applications

Refrigeration, air conditioning and electrical industry, plumbing technology.

Operating conditions

Silver based brazing alloy with excellent flow, capillarity and mechanical strength characteristics. Used for brazing any steels, copper and copper alloys, as well as nickel and nickel alloys.

Recommended fluxes

N1/T, Super 1, N2/E, H paste, RS/A, FN/E, D 98, H 280.

Heat sources

Induction heating, flame, furnace in vacuum and under protective atmosphere.

Delivery forms

Wire, rods, ribbon, rings, preforms, powder.

Notes

AWS A5.8 (ASME IX): BAg-34.

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations. Italbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of surface and instability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.