



Brazing alloy in paste Degufit 3000

Composition (% in weight)

Ag	Cu	Zn	Sn	Si	P	Mn	Ni	Other	EN ISO 9453	EN 1044:1999	ISO 3677
-	3	-	Rest	-	-	-	-	-	402 ref. metallic part	-	S-Sn97Cu3

Technical data:

Melting range (°C)	227-310
Working temperature (°C)	-
Boiling point (°C)	-
Flash point (°C)	-
Operating temperature of brazed joint (°C)	-
Tensile strength DIN EN 12797 (MPa)	-
Alloy density (g/cm³)	7,3
Paste density (g/cm³)	2,4
Metal content (%) of total weight	60
Chloride content (%)	Max. 9
Viscosity (dPas)	300-500 (Haake Viscotester 02, Sp.2, 20 ± 2°C)
Cleaning agent	Water
Flux type within the paste	DIN EN 9454-1:3.1.1.4
Shelf life	24 months, but only in the original sealed container at storage temperatures between +5° to 30°C

Applications

Plumbing technology, electrical industry

Operating conditions

Tin based brazing alloy. Excellent flow, capillarity and mechanical strength characteristics. Used for joining copper, copper alloys, steel, as well as nickel and nickel alloys. Degufit 3000 meets the requirements of the working sheet "GW2" and "GW 7" of DVGW (German Association of Gas and Water). It is approved and registered by DVGW (DV-0101AU2229) and has been awarded by the Gütegemeinschaft Kupferrohr e.V. (The coppertube Manufactures Quality Association). Therefore it is suitable for copper pipes installations for plumbing system.

Heat source

Flame, induction heating

Standard packaging

250 gr jar with brush

Notes

Clean the joint from metal oxides through mechanical rubbing. Apply a thin layer of paste on the cleaned tube surface. After assembling the joint, heat with flame or resistance till fillet appears. During brazing process, add alloy BrazeTec 3 in wire. Paste residues must be removed by mechanical rubbing or washing with water. Potable water lines have to be rinsed referring DIN 1988 in.

The information reported in this document about our products and equipment as well as our systems and procedures are based on our research and our experience in the field of applied engineering and are merely recommendations. Italbras S.p.A. cannot foresee all circumstances in which these information and our products will be used, therefore the user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. Italbras S.p.A. declines any liability for any loss, damage or injury howsoever arising (including any claim brought by third parties) as a result of the use of such information. Each warranty of suitability of our products and their use within the production processes of the user, must be agreed in written form. We reserve the right to make technical modifications to this document in the course of our product development.